

Classifications

EN ISO 3581-A	AWS A5.4 / SFA-5.4
E 22 12 B 2 2	E309-15

Characteristics and typical fields of application

Basic core wire alloyed electrode of E 22 12 B / E309-15 type for welding austenitic heat resistant rolled, forged and cast steels as well as heat resistant ferritic CrSiAl steels, e.g. in annealing plants, hardening plants, steam boiler construction, the crude oil industry and the ceramics industry. Scaling resistant up to 950°C. For weld joints exposed to reducing, sulphurous gases, the final layer has to be deposited by means of BÖHLER FOX FA.

Atmosphere	Max. application temperature in °C		
	Sulfur-free	Max. 2 g S/Nm ³	> 2 g S/Nm ³
Air and oxidizing combustion gases	950	930	850
Reducing combustion gases	900	850	

Base materials

1.4710 GX30CrSi6, 1.4713 X10CrAl7, 1.4724 X10CrAl13, 1.4742 X10CrAl18, 1.4740 GX40CrSi17,
1.4828 X15CrNiSi20-12, 1.4826 GX40CrNiSi22-9, 1.4833 X7CrNi23-14
AISI 305, 309, 405,
UNS S40500, S30900, ASTM A297 HF

Typical analysis


	C	Si	Mn	Cr	Ni
wt.-%	0.1	1.0	1.1	22.5	12.2

Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength R _{p0.2}	Tensile strength R _m	Elongation A (L ₀ =5d ₀)	Impact energy ISO-V KV J
	MPa	MPa	%	20°C
u	450 (≥ 350)	610 (≥ 550)	40 (≥ 25)	90

u untreated, as welded

Operating data

	Polarity	DC+	Dimension mm	Current A
	Electrode identification	FOX FF E 22 12 B	2.5 × 300	50 – 75
			3.2 × 350	80 – 105
			4.0 × 350	110 – 140
			5.0 × 450	140 - 190

Preheating and interpass temperatures for ferritic steels 200 – 300°C.
Suggested heat input max. 1.5 kJ/mm.

Approvals

TÜV (09090), CE