

PRODUCT DATA SHEET

Sikagard®-6060 S

SPRAYABLE BITUMEN BASED UNDERBODY COATING IN AEROSOL CAN

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Bitumen solution
Color (CQP001-1)	Black
Cure mechanism	Air-drying
Solid content	33 %
Application temperature	15 – 25 °C
Film thickness	wet 400 µm dry 150 µm
Tack free time	75 minutes ^A
Drying time	2.5 h ^A
Service temperature	-25 – 80 °C
Shelf life	24 months ^B

CQP = Corporate Quality Procedure

^A) 23 °C / 50 % r. h.^B) storage between 5 °C and 25 °C**DESCRIPTION**

Sikagard®-6060 S is a fast-drying, bitumen-based quick repair protective coating in an aerosol can with very good rust-proofing and sound deadening properties. It is suitable for an effective vehicle underbody protection. Sikagard®-6060 S can be sprayed haze free without any cob webbing and does not drip. Sikagard®-6060 S shows good adhesion on different paints, metal primers, metals and PVC without any pre-treatment.

A tough coating remains after drying, protecting metal from corrosion.

PRODUCT BENEFITS

- Equipment independent (aerosol). Easy to use.
- Outstanding application properties (no running or dripping)
- Good adhesion performance to a wide variety of substrates
- Excellent acoustic and damping properties
- fast drying
- Road salt resistant
- High solid content

AREAS OF APPLICATION

Sikagard®-6060 S is a spray applied anti-corrosion coating for quick repairs of non-visible areas such as wheel arches and underbody parts of vehicles that do not need to be over painted.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

PRODUCT DATA SHEET

Sikagard®-6060 S

Version 01.01 (01 - 2020), en_DK

013913010603001100

CHEMICAL RESISTANCE

Sikagard®-6060 S is resistant against water, seawater, salt spray, bases and acids. The above information is offered for general guidance only. Advice on specific applications will be given on request.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal substrates must be pretreated to enhance corrosion resistance (e.g. uncoated steel, etc).

Application

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Spray at room temperature and from a distance of approx. 25 cm in an grid motion to build up a continuous coat.

Sikagard®-6060 S can be applied without dripping. If a thick layer is required, let layers dry in between. Hold the can in an upright position and do not spray on parts of the brake, engine or exhaust system.

After use, invert can and spray in short bursts to clear nozzle.

Removal

Uncured Sikagard®-6060 S can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once dried, the material can only be removed mechanically. Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

Sikagard®-6060 S cannot be overpainted.

FURTHER INFORMATION

Copies of the following publication is available on request:

- Safety Data Sheet

PACKAGING INFORMATION

Aerosol can	500 ml
-------------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

Any information or suggestions for use concerning Sika's products, which we either in writing or orally have given buyers or end-users of the product, have been given in good faith based on our own experiences and based on approved praxis and the technological and scientific knowledge on the time of giving such suggestions and information, which are given without any type of guarantees, and which do not lead to any further responsibility from Sika Danmark A/S, besides what is stated in the sales agreement in question. The buyer or end-user should themselves investigate or otherwise make sure, that our products are suitable for the use in question and further make sure that the products are kept and used correct and in agreement with the published rules and considering the actual conditions in order to avoid damages or less satisfactory results. Any order is accepted and any deliverance is affected according to the general terms of sales and delivery from Sika Danmark A/S, which are considered known and accepted, and which could be handed out when asked for. Our catalogues are not up-dated automatically. The present product data sheet is only for use in Denmark. Values stated in the present product data sheet should be seen as recommended, unless stated otherwise.

PRODUCT DATA SHEET

Sikagard®-6060 S
Version 01.01 (01 - 2020), en_DK
013913010603001100

Sika Danmark A/S
Hirsemarken 5
3520 Farum
Tlf. +45 48 18 85 85
www.sika.dk

